

TECHNICAL DATA SHEET
CRUM RUBBER MODIFIED BITUMEN

SL No.	Parameters	Specifications			Testing Method
		CRMB-50	CRMB-55	CRMB-60	
1	Penetration at 25 °C 0.1mm, 100 gm, 5 Sec	60-120	50-80	30-50	IS:1203-1978
2	Softening Point R&B (°C) Min	50	55	60	IS:1205-1978
3	Flash Point , COC, °C Min	220	220	220	IS:1209-1978
4	Elastic Recovery of Half Thread in Ductilometer at 25 °C % min	50	60	60	IRC:SP53-2002-I
5	Separation difference in Softening Point, R & B , °C Max	3	3	3	IRC:SP53-2002-II
6	FRASS Breaking Point °C Maximum	-20	-16	-12	RC:SP:53-2010

